

## BubbleTex® 18mm – 4500g/m<sup>2</sup>

Properties	Units	Values	Test Method
Grammage	g/m <sup>2</sup>	4.500	
Thickness	mm	18,0	
Density	Kg/m <sup>3</sup>	250	
Elastic Modulus (Transversal)	MPa	640,0	Iso 178
Elastic Modulus (Longitudinal)	MPa	635,0	Iso 178
Bending resistance (Transversal)	MPa	19,0	Iso 178
Bending resistance (Longitudinal)	MPa	6,0	Iso 178
Tensile Strength (Transversal)	MPa	5,0	Iso 527
Tensile Strength (Longitudinal)	MPa	6,0	Iso 527
Odour (2h at 110° C)	No perceptible odour		
Chemical resistance	PP typical		

	Weight	Thickness	Width	Length	Pallet Flatness
Tolerances	± 10%	± 3%	± 1%	± 2%	max 30 mm

Standard Sheet Sizes: 1220 x 2440 x 18mm and 1500 x 3000 x 18mm  
 Standard Weight Configuration is 4500g/m<sup>2</sup>

13mm/3.000g/sqm

15mm/4.000g/sqm

17mm/5.000 g/sqm

The obtained results and the properties above refer to average values of lab tests on samples of our standard production. It is understood that entails no obligation and/or responsibility on Corrugated Plastic Products Ltd. Customers should verify the suitability of the product for its specific end-use.